



DIRECTIONS FOR USE

ROOF TREATMENT

Surface Preparation

Proper surface preparation is the key to maximum performance. The appearance and durability of this product can be impaired by an unsound or poorly prepared surface. In order to be effective, this finish must be able to penetrate. It is especially important that the surface be clean of all dirt, mildew, loose wood fibers and other foreign matter. Surfaces must be structurally sound. Previously finished shakes/shingles should be either media blasted, or chemically stripped with Timber Pro Strip & Brite. Weathered wood shakes/shingles must be power washed using a wide fan tip and low pressure to clean and restore the surface to new wood condition. New shakes/shingles should be power washed in the same method as above.

Precautions

Do not apply if rain or freezing temperature is likely to occur. Apply to a cool surface and avoid application in direct sunlight. Protect from freezing.

Stirring

Stir the product well before commencing and occasionally during use. If the product requires more than one batch, blend them together. Before commencing the entire job, always test for appearance and colour in an inconspicuous spot.

To avoid non-uniform appearance

Start at one edge or roof and follow through to a logical break, such as end of roof plane or dormer.

Method of application

Stirring: Stir thoroughly before and occasionally during use. If the job requires more than one batch, blend them together. Before proceeding with entire job always test for appearance and color in an inconspicuous area.

Number of Coats

Apply one saturated colour or clear coat of Roof Treatment. Apply as much product as shingle/ shake will absorb but do not leave any puddling, pooling or runs. Thoroughly back brush to ensure proper dispersion and penetration into shingle/shake surface. Roof Treatment is designed as a "one coat" application. A second coat can be applied after the first coat has thoroughly dried. A second coat will enhance protection and offer extended interval between maintenance coats

Coverage Per Coat

On rough sawn shingles or shakes coverage is between 7 – 11.5 m² per gallon (75-125 sq ft per gallon). Smooth shingle or shake coverage is 9-14 m² per gallon (100-150 sq ft per gallon).

Maintenance

Depending upon exposure or wear, evaluate recoating needs every 2-5 years. Re-Apply Roof Treatment as needed to maintain and protect shingles and shakes.

Clean Up

Clean Up: Clean brushes and equipment with soap and water.

THE COMPLETE LINE OF TIMBER PRO PRODUCTS

Timber Pro Coatings Canada
Unit 140, 12051 Horseshoe Way, Richmond BC, V7A 4V4
Tel: 604-270-4244 email: canadainfo@timberprocoatings.com

Warranty

When applied to new wood according to the label directions. If this Timber Pro product is proved to be defective after purchase Timber Pro Coatings Ltd. will furnish any necessary additional product free of charge or will refund the purchase price at the company's option. This warranty does not include labor or coat of labor. For the application of the product, this warranty gives you specific legal rights. And you may also have other rights that vary from country to country.

www.TimberProCoatings.ca
www.TimberProCoatings.com