



DIRECTIONS FOR USE

CRYSTAL URETHANE

Surface Preparation

Proper preparation is the key to maximum performance. The appearance and durability of this product can be impaired by an unsound or poorly prepared surface. In order to be effective, the finish must be able to penetrate. It is very important that the surface be clear of all dirt and mildew, loose wood fibers and other foreign matter. Surfaces must be structurally sound. Previously finished or weathered wood surfaces must be either sanded, or chemically stripped with Timber Pro Strip & Brite. New wood that appears shiny millglazed must be sanded 60-80grit.

Precautions

Do not apply if rain or freezing temperature is imminent. Do not apply in direct sunlight or to hot surfaces. Do not apply above 25 °C (80 °F). Do not thin the product. Protect from freezing.

Stirring

Stir the product well before commencing and occasionally during use. If the product requires more than one batch, blend them together. Before commencing the entire job, always test for appearance and colour in an inconspicuous spot. To assure uniform appearance and avoid lap marks. Start at one edge and follow through to a logical break, the end of the board for example.

Method of application

Apply by nylon polyester brush, spray or paint pad. Apply a generous coat and smooth out any runs, drips or puddles. When spraying, always back brush immediately after each section to assure proper penetration.

Number of Coats

Apply 2 coats of Timber Pro Ultra DF Formula allow 16 hours dry between coats and at least 16 hours prior to heavy foot traffic. For lower lying decks or decks subject to heavy moisture exposure 1 coat is recommended.

Coverage Per Coat

Smooth wood coverage is approximately 6.1-7.4 m² per liter (250-300 sq ft/gallon). Rough wood coverage is approximately 3.1-3.5 m² per liter (125-150 sq ft/gallon). Coverage will vary depending on an age or surface porosity.

Maintenance

Due to the high wear and constant exposure of decks to the elements this application may require more frequent application. An annual inspection is recommended and application of Timber Pro Ultra DF Formula every 12-18 months. Do not allow snow to accumulate on decks for any long length of time. In the case of fences a maintenance of coat of Timber Pro Ultra DF Formula is recommended every 2-3 years or on south and west side and 3-4 years on north and east side.

Depending on the amount of exposure, more frequent application may be necessary.

Clean Up

Clean Up: Clean brushes and equipment with soap and water.

THE COMPLETE LINE OF TIMBER PRO PRODUCTS

Timber Pro Coatings Canada
Unit 140, 12051 Horseshoe Way, Richmond BC, V7A 4V4
Tel: 604-270-4244 email: canadainfo@timberprocoatings.com

Warranty

When applied to new wood according to the label directions. If this Timber Pro product is proved to be defective after purchase Timber Pro Coatings Ltd. will furnish any necessary additional product free of charge or will refund the purchase price at the company's option. This warranty does not include labor or coat of labor. For the application of the product, this warranty gives you specific legal rights. And you may also have other rights that vary from country to country.

www.TimberProCoatings.com