



DIRECTIONS FOR USE TIMBER SEAL

Surface Preparation

Proper surface preparation is the key to maximum performance. The appearance and durability of this product can be impaired by an unsound or poorly prepared surface. In order to be effective, this finish must be able to penetrate. It is very important that the surface be clean of all dirt, mildew, loose wood fibers and other foreign matter. Surfaces must be structurally sound. Previously finished or weathered wood surfaces must be either sanded or chemically stripped with Timber Pro Strip & Brite or power washed to restore the surface to new wood condition. New wood that appears shiny or weathered wood with an uneven surface should be sanded with 60 or 80 grit sand paper to remove mill glaze and level the surface. Rinse or blow off sanding dust prior to applying Timber Seal. New rough cut lumber should be power washed. New logs should be power washed and/or sanded.

Precautions

Do not apply if rain or freezing temperature is likely to occur. Apply to a cool surface and avoid application in direct sunlight, on very warm days, cool wood surface by lightly and evenly misting with cold water (no puddles). Apply finish soon after misting while surface is damp. Protect from freezing.

Stirring

Stir thoroughly before and occasionally during use. If the job requires more than one batch, blend them together. Before proceeding with entire job always test for appearance and color in an inconspicuous area.

Method of application

Apply by spray, brush, roller, dip tank, or paint pad. Flood coat surface and then smooth out all runs, drips and puddles. When spraying or rolling, always back-brush immediately after each section is coated to ensure proper penetration.

To avoid non-uniform appearances

To avoid non-uniform appearances: On vertical siding start at top with several boards and continue all the way to the bottom. On horizontal siding and/or logs start at bottom and work up. Start at one edge and follow through to a logical break, such as a door, window or corner. For Decks and Docks, apply product liberally in the direction boards are installed. Back brush excessive Timber Seal to avoid leaving pooled or puddled material on surface. Siding, Deck and Dock boards can be prefinished prior to installation. Be sure to saturate all 6 sides and allow material to dry prior to installation.

Number of Coats

For exterior surfaces; apply one saturated coat or a wet on wet coat. (Wet on wet coat has to be applied with-in 15 minutes of first coat). Apply as much product as wood will absorb but do not leave any pooling, puddling or runs. Thoroughly back brush to ensure proper dispersion and penetration into wood surface.

Coverage Per Coat

On rough sawn wood coverage is between 3.5-5 m² per liter (150-200 sq ft per gallon). Smooth wood coverage is 6.1-7.4 m² per liter (250-300 sq ft/gallon). Exotic woods (hardwoods) coverage is between 7.4-9.8 m² per liter (300-400 sq ft /gallon). Aged porous wood requires coverage between 3.5-5m² per liter (150-200 sq ft per gallon). Coverage may vary depending on the porosity of the wood.

Maintenance

Depending upon exposure or wear; evaluate recoating needs every 2-4 years. Timber Seal Formula can be applied on an as needed basis as part of an ongoing maintenance program.

Clean Up

Clean Up: Clean brushes and equipment with soap and water.

THE COMPLETE LINE OF TIMBER PRO PRODUCTS

Timber Pro Coatings Canada
Unit 140, 12051 Horseshoe Way, Richmond BC, V7A 4V4
Tel: 604-270-4244 email: canadainfo@timberprocoatings.com

Warranty

When applied to new wood according to the label directions. If this Timber Pro product is proved to be defective after purchase Timber Pro Coatings Ltd. will furnish any necessary additional product free of charge or will refund the purchase price at the company's option. This warranty does not include labor or coat of labor. For the application of the product, this warranty gives you specific legal rights. And you may also have other rights that vary from country to country.

www.TimberProCoatings.com