



DIRECTIONS FOR USE YARD TREATMENT

Surface Preparation

The surface must be relatively free from dirt, discoloration, and loose fibers. The cambium layer must be removed to allow the Log Yard Treatment to penetrate into the logs. Protect, cover, or mask all nearby surfaces not being treated.

Precautions

Do not apply if rain or freezing temperature is likely to occur. Do not allow the product to freeze.

Stirring

Stir contents well.

Method of application

Saturate the wood using a low-pressure sprayer. Apply the product heavily either on a low-pressure garden-type sprayer or HVLP sprayer. Higher-pressure sprayers tend to atomize the product resulting in loss of product. Allow the product to absorb, and then brush out any runs or drips.

Number of Coats

Apply 2 coats of Timber Pro Ultra DF Formula allow 16 hours dry between coats and at least 16 hours prior to heavy foot traffic. For lower lying decks or decks subject to heavy moisture exposure 1 coat is recommended.

Coverage Per Coat

Log Yard Treatment covers approximately 250-350 sq. ft/gallon depending on wood surface porosity.

Drying Time

Drying time approximate 16 hours, depending on humidity and temperature.

Clean Up

Clean Up: Clean up overspray, drips and splashes immediately with water. Clean all tools & application equipment with soap & water.

THE COMPLETE LINE OF TIMBER PRO PRODUCTS

Timber Pro Coatings Canada
Unit 140, 12051 Horseshoe Way, Richmond BC, V7A 4V4
Tel: 604-270-4244 email: canadainfo@timberprocoatings.com

Warranty

When applied to new wood according to the label directions. If this Timber Pro product is proved to be defective after purchase Timber Pro Coatings Ltd. will furnish any necessary additional product free of charge or will refund the purchase price at the company's option. This warranty does not include labor or coat of labor. For the application of the product, this warranty gives you specific legal rights. And you may also have other rights that vary from country to country.

www.TimberProCoatings.com